



PRODUCT INFORMATION DATA SHEET

ANTISTAT - 9500

Internal Antistatic Agent for Thermoplastic Polymers

DESCRIPTION : Fatty Acid Ester

SPECIFICATIONS : Appearance : White beads/Powder
Acid Value : 3.0 Max.
Iodine Value : 2.00 Max.
Melting Point : $65 \pm 5^{\circ}\text{C}$

PROPERTIES : ✍ **ANTISTAT - 9500** is generally recognized as safe for food contact applications.
✍ High polarity permits lower usage levels in Polyolefins
✍ Rapid action - effective antistat
✍ Outstanding thermal stability
✍ No yellowing/discoloration
✍ Ensures fast mould filling
✍ Reduced cycle times
✍ Easy release

APPLICATIONS : **ANTISTAT - 9500** is one of the most important and widely used Antistatic agent. **ANTISTAT - 9500** is a new generation, high activity Nitrogen free Antistat/Lubricant, specially effective in providing static electricity control in a large variety of Thermoplastic Polymers like Polypropylene, Polyethylene, Polyvinyl Chloride etc.

SUGGESTED USE LEVELS:

0.1% to 0.5 % for LDPE/LLDPE films
0.2% to 0.5 % for PP films
0.3% to 2.0 % for PP injection / HDPE moulded items.
0.5 % to 1.0 % for EPS moulding.
0.5 % to 1.0 % for plasticized PVC
3.0 % to 5.0 % for rigid PVC

continue 2/-



... 2 ...

PERFORMANCE OF ANTISTAT- 9500 IN VARIOUS PLASTIC

POLYMER	USE LEVEL	SURFACE RESISTIVITY (ohms)*
LLDPE	0.2 %	3.10 ¹⁰
LDPE	0.5 %	2.10 ¹⁰
HDPE	1.5 %	2.10 ¹¹
PP (Homopolymer)	2.0 %	7.10 ⁹
Rigid PVC (Tin stabilized)	3.0 %	2.10 ¹¹
Rigid PVC (Ca-Zn stabilized)	2.0 %	4.10 ¹⁰