



## PRODUCT INFORMATION DATA SHEET

# LIBNOL G-21

**DESCRIPTION** : Oleochemical Derivative

**SPECIFICATIONS** : Appearance : Creamish Powder/Flakes  
Acid Value : 3 Max.  
Iodine Value : 3 Max.  
Melting Point : 58°C ± 5°C

**APPLICATIONS** : ✍ Processing rigid and Semi rigid PVC  
✍ By Extrusion, Injection moulding.

***Specially suggested for use in Manufacturing of***

✍ Rigid PVC Pipes/Profiles/Conduits, Rigid PVC Fittings/Moulded Parts, PVC Cable/Footwear Compounds

**PROPERTIES** : ✍ Intermediate Lubricant  
✍ Good Compatibility

**DOSAGE** : 0.5 - 1.5 phr for Rigid PVC  
0.5 - 1.0 phr for Semi Rigid PVC

**STABILISATION** : Suitable for use with all commercially -available stabilizers.  
(Pb,Tin, Ba-cd, Ba-zn etc.)